



HYLOMAR JOINTING COMPOUND

**Non-setting jointing compound for flanged joints
Primarily for Mineral oil, Petrol, Diesel, Paraffin, Air & Water**

FEATURES

- Ø Temperature range -50°C to 250°C
- Ø Suitable for pressures up to 500 psi (35 bar)
- Ø Hylomar grade: Universal Blue
- Ø Effective sealing of metal to metal & most plastic to plastic components
- Ø Non-setting, Non-hardening
- Ø Resists vibration and thermal expansion
- Ø Particularly suited to Automotive Industry applications

DIRECTIONS FOR USE

- Ø Do not apply in sub-zero temperatures
- Ø Ensure surfaces are clean and free of contaminants
- Ø Apply by brush or hand
- Ø Assemble within 15 minutes
- Ø Pressure test after a minimum of 30 minutes at ambient ($20-25^{\circ}\text{C}$)

Technical and Safety Data Sheets are available from:

Fax Back Facility : +44 (0)113 232 2770
Web Site : www.rocol.com
Customer Service : +44 (0)113 232 2700

Issue 28060b – May-04

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

www.rocol.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers.
There are many factors outside our control or knowledge which affect the use and performance
of our products, for which reason it is given without responsibility.



HYLOMAR JOINTING COMPOUND

TECHNICAL DATA (typical values)

Appearance	Soft blue paste
Base type	Polyester urethane & solvent
Solids	Silica
Temperature	-50°C to 250°C
Pressure	Up to 500 psi (35 bar)
Thickness of residue	0.03 mm
Surface finish (Ra)	3.0 micron (max)
Area covered by 100g	1.125 m ²
Suitable applications	Most Industrial fuels & oils Air, Water & Brine Turbine & piston engine combustion products Water/glycol and methanol mixtures Petroleum & diester lubricating oils Gasoline & kerosene (paraffin) fluids Some fluorocarbon refrigerants
Storage	Storage temperature should be controlled to between 5 and 30 °C.
Pack sizes	100g

Issue 28060b – May-04

2

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

www.rocol.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA